

Attorney's Docket No.: 06618-406001

OFFICIAL COMMUNICATION
FACSIMILE
FOR THE PERSONAL ATTENTION OF:
EXAMINER

GROUP 1700 FAX NO: 703-872-9310

Number of pages including this page 9

Applicant : S.R. Narayanan et al.
Serial No. : 09/489,514
Filed : January 21, 2000

Art Unit : 1745
Examiner : J. Mercado

FACSIMILE COMMUNICATION
Title : MEMBRANE-ELECTRODE ASSEMBLIES FOR DIRECT METHANOL FUEL
CELLS

Commissioner for Patents
Washington, D.C. 20231

Sir:

Attached to this facsimile communication cover sheet is Response to Office
Action faxed this 8th day of April, 2002, to Group 1745, the United States Patent and Trademark
Office.

Respectfully submitted,

Date: April 8, 2002

Dorothy P. Whelan
Dorothy P. Whelan
Reg. No. 33,814

Fish & Richardson P.C., P.A.
60 South Sixth Street
Suite 3300
Minneapolis, MN 55402
Telephone: (612) 335-5070
Fax: (612) 288-9696

60080041.doc

NOTE: This facsimile is intended for the addressee only and may contain privileged or confidential
information. If you have received this facsimile in error, please immediately call us collect at
(612) 335-5070 to arrange for its return. Thank you.

Received from <6122889696> at 4/8/02 10:00:51 AM [Eastern Daylight Time]

Attorney's Docket No.: 06618-406001

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant : S.R. Narayanan et al. Art Unit : 1745
Serial No. : 09/489,514 Examiner : Julian Mercado
Filed : January 21, 2000
Title : MEMBRANE-ELECTRODE ASSEMBLIES FOR DIRECT METHANOL FUEL
CELLS

VIA FACSIMILE
Commissioner for Patents
Washington, D.C. 20231

AMENDMENT

In response to the action mailed December 11, 2001, please amend the application as follows:

In the claims:

Please amend claims 7, 13, 15, 16, and 18-20 as follows:

B1 7. (Amended) A process for making a catalyst ink for a fuel cell, comprising mixing, at room temperature, components comprising water, particles of a fluorocarbon polymer with a particle size of 1 to 4 microns, and a catalytic material.

B2 13. (Amended) A process for making an electrode assembly for a fuel cell, comprising:
(a) providing a catalyst ink comprising water, particles of a fluorocarbon polymer with a particle size of 1 to 4 microns, and a catalytic material; and
(b) applying the catalyst ink at room temperature to at least one side of a substrate.

B3 15. (Twice Amended) The process of claim 14, further comprising roughening the side of the membrane prior to applying the catalyst ink.

CERTIFICATE OF TRANSMISSION BY FACSIMILE

I hereby certify that this correspondence is being transmitted by facsimile to the Patent and Trademark Office on the date indicated below.

April 8, 2002

Date of Transmission

Signature

Diane Wimperis

Diane Wimperis

Typed or Printed Name of Person Signing Certificate